



3 Strand Natural Fiber Manila Rope

The strongest of all natural fiber ropes. It is resistant to heat, sunlight, and abrasion and has low stretch. Commonly used for construction and decorative purposes.



3 Strand Natural Fiber Manila Rope

Part Number	Diameter (in.)	Length (ft.)	Package Type	Minimum Break Strength (lbs.)	Approximate Density (lbs./100 ft.)	Approximate Package Weight (lbs.)
TWM080100	1/4	100	Coillette	540	2.0	2.0
TWM080600	1/4	600	Carton	540	2.0	12.0
TWM081200	1/4	1,200	Carton	540	2.0	24.0
TWM100600	5/16	600	Carton	900	2.9	17.4
TWM101200	5/16	1,200	Carton	900	2.9	34.8
TWM120100	3/8	100	Coillette	1,215	4.1	4.1
TWM120600	3/8	600	Carton	1,215	4.1	24.6
TWM121200	3/8	1,200	Carton	1,215	4.1	49.2
TWM160100	1/2	100	Coillette	2,385	7.5	7.5
TWM160600	1/2	600	Carton	2,385	7.5	45.0
TWM161200	1/2	1,200	Carton	2,385	7.5	90.0
TWM200100	5/8	100	Coillette	3,960	13.3	13.3
TWM200600	5/8	600	Carton	3,960	13.3	79.9
TWM201200	5/8	1,200	Carton	3,960	13.3	160.0
TWM240100	3/4	100	Coillette	4,860	16.6	16.6
TWM240600	3/4	600	Carton	4,860	16.6	99.6
TWM241200	3/4	1,200	Coil	4,860	16.6	199.0
TWM280600	7/8	600	Coil	6,930	22.5	135.0
TWM281200	7/8	1,200	Coil	6,930	22.5	270.0
TWM320100	1	100	Coil	8,100	27.0	27.0
TWM320600	1	600	Coil	8,100	27.0	162.0
TWM321200	1	1,200	Coil	8,100	27.0	324.0
TWM340100	1-1/4	100	Coil	12,150	41.8	41.8
TWM340600	1-1/4	600	Coil	12,150	41.8	251.0
TWM360100	1-1/2	100	Coil	16,650	60.0	60.0
TWM360600	1-1/2	600	Coil	16,650	60.0	360.0
TWM400100	2	100	Coil	27,900	107.0	107.0
TWM400600	2	600	Coil	27,900	107.0	642.0
TWM960100	3	100	Reel	57,600	241.0	241.0
TWM960300	3	300	Reel	57,600	241.0	723.0
TWM960600	3	600	Coil	57,600	241.0	1,446.0

